
Our Boards

Premium Yakisugi (Charred Wood) Cladding available in three finishes:
Hakuu (exposed char without brushing), Benii (light-brushed smooth),
and Sumii (hard-brushed striped pattern).

- | | |
|---------------------------------|---|
| · Storage Considerations | <ul style="list-style-type: none">-Protect against damage and discoloration-Do not expose to direct sunlight or rain-Separate bundles to promote air-circulation-Acclimate at Project Site for at least 14 days prior to installation-Maximum moisture content at installation: 14% |
|---------------------------------|---|
-

- | | |
|-----------------|--|
| · Finish | <p>Factory-finish options:
Touch-up Cream color options
Available in black, clear and custom colors.</p> |
|-----------------|--|
-

- | | |
|--------------------|--|
| · Treatment | <p>Charred wood (Yakisugi) process</p> |
|--------------------|--|
-

- | | |
|---------------------------|--|
| · Serviceable life | <p>30 years or more when maintained according to manufacturer's recommendations.</p> |
|---------------------------|--|
-

- | | |
|------------------|--|
| · Species | <p>Japanese Cypress (Cryptomeria Japonica)</p> |
|------------------|--|
-

- | | |
|-------------------------------------|---|
| · Cleaning & Maintenance | <ul style="list-style-type: none">-Wipe exposed surfaces with clean, wet rag to remove soil-Touch-up field cuts and damaged factory-applied finishes-Clean and repair any soiled or damaged areas |
|-------------------------------------|---|

· Warranty**-Manufacturer's Limited Warranty:**

10-year warranty against manufacturing defects
Covers delamination and structural failure
Excludes natural wood characteristics and weathering
Warranty void if installation guidelines not followed

-Installation Warranty:

Requires installation by certified contractors
Must follow manufacturer's written installation instructions
Proper ventilation and moisture barriers required
Regular maintenance according to care instructions

-Warranty Conditions:

Product must be stored and installed according to specifications
Moisture content must not exceed 14% at installation
Proper finishing and maintenance required
Documentation of installation methods and materials required
Claims must be submitted in writing within warranty period

Note: This warranty does not cover:

Natural wood characteristics (grain variation, knots)
Normal weathering, wear and tear
Damage from improper handling or installation
Damage from extreme weather events
Failure to follow maintenance guidelines

· Moisture content

Maximum 14% at time of installation

· Expected Dimensional Change

-Width: ~2-3% expansion
-Length: ~0.25-0.3% expansion
-Thickness: ~2.4-6.4% expansion
*Measured from 7% moisture content to fiber saturation. Individual boards may show variation.

· Average density

360-420 kg/m³

· **Hardness** Low (320-500 lbf Janka)

· **Weight** ~11 kg/m2

· **Certification** PEFC

P +61 0401 270 818
E contact@studiotsukuru.com.au
W studiotsukuru.com.au